

IN THE CLAIMS:

1. (PREVIOUSLY PRESENTED) A polymer composition comprising:
a first component being an adipic polyester;
a second component being a natural polymer; and
a third component being a thermoplastic polyester, wherein the first component, second component and third component are combined to form the polymer composition.
2. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the natural polymer is starch.
3. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 2 wherein the starch is granular.
4. (CANCELED)
5. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the thermoplastic polyester is at least one of poly(lactic acid), cellulose acetate, polycaprolactone, polyhydroxy(butyrate-co-valerate)(PHBV), poly(butylene succinate adipate), poly(butylene succinate), aliphatic-aromatic copolymer, and poly(ethylene terephthalate)(PET).
6. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the second component is present in an amount up to about 74 wt.%.

7. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the first component is present in an amount up to about 40 wt.%.

8. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the third component is present in an amount up to about 80 wt.%.

9. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 including a fourth component being at least one of an external lubricant, nucleating agent and plasticizer.

10. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the natural polymer has a moisture content of less than about 15 wt.%.

11. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is biodegradable.

12. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is processed into an article that keeps its shape at temperatures of up to and more than about 100°C.

13. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is annealed to increase high temperature stability.

14. (CANCELED)

15. (CANCELED)

16. (CANCELED)

17. (CANCELED)

18. (CANCELED)

19. (CANCELED)

20. (CANCELED)

21. (CANCELED)

22. (CANCELED)

23. (CANCELED)

24. (CANCELED)

25. (CANCELED)

26. (CANCELED)

27. (CANCELED)

28. (CANCELED)

29. (CANCELED)

30. (CANCELED)

31. (CANCELED)

32. (CANCELED)

33. (CANCELED)

34. (CANCELED)

35. (CANCELED)

36. (CANCELED)

37. (CANCELED)

38. (CANCELED)

39. (CANCELED)

40. (CANCELED)

41. (PREVIOUSLY PRESENTED) A polymer composition comprising:

a first component being a hydroxy-functional polymer;

a second component being a natural polymer; and

a third component being a thermoplastic polyester, wherein the first component, second component and third component are combined to form the polymer composition and wherein the hydroxy-functional polymer is a poly(hydroxy ester ether)(PHEE) in an amount of about 1 wt.%.